




PATENT

IN THE CLAIMS:

Please amend the claims as follows:

RECEIVED
CENTRAL FAX CENTER
SEP 26 2006

1. (Currently amended) A composition comprising the product of combining, in the presence of a free radical initiator, a catalyst precursor and at least one monomer wherein the monomer is polymerizable by free-radical polymerization, and wherein the catalyst precursor is represented by one of the formulas:



wherein

- (a) M is titanium;
M¹ is titanium;
- (b) L_A is a substituted or unsubstituted, cyclopentadienyl or heterocyclopentadienyl ligand connected to M or M¹ wherein L_A comprises R;
- (c) L_B is a ligand as defined for L_A but selected independently of L_A;

Page 2 of 23

I:\Bpc\LAW\Prosecution\EMCC Prosecution\2002\2002B181B\2002B181B US\2002B181B-US-2006Aug22-1.116 response.doc

PAGE 5/29 * RCVD AT 9/26/2006 5:00:13 PM [Eastern Daylight Time] * SVR:USPTO-EFAX-1/7 * DNIS:2738300 * CSID:281 834 1231 * DURATION (mm:ss):06:28

BEST AVAILABLE COPY

PATENT

(d) T is a bridging group that connects L_A and L_B and comprises a Group-13-to-16 element and 0-2 of R' ; and

(e) D and E are the same or different abstractable ligands,

wherein ~~each R , R' , and R''~~ R and R' are independently hydrogen or a hydrocarbyl group provided at least one of ~~R , R' , and R''~~ R and R' can be polymerized by a free radical initiator.

2. (Currently amended) The composition of Claim 1 wherein ~~each R , R' , and R''~~ R and R' are independently hydrogen or a C_1 - C_{50} hydrocarbyl group.
3. (Currently amended) The composition of Claim 1 wherein ~~each R , R' , and R''~~ R and R' are independently hydrogen or a C_1 - C_{20} hydrocarbyl group.
4. (Previously presented) The composition of Claim 3 wherein each R is independently one of hydrogen, allyl, methyl, or a phenyl group.
5. (canceled)
6. (canceled)
7. (Previously presented) The composition of Claim 3 wherein the abstractable ligands are independently hydride radicals; hydrocarbyl radicals; or hydrocarbyl-substituted organometalloid radicals.
8. (Previously presented) The composition of Claim 7 wherein two of the abstractable ligands join to form a 3-to-40-atom metallacycle ring.
9. (Previously presented) The composition of Claim 3 wherein the abstractable ligands are independently halogen, alkoxide, aryloxy, amide, or phosphide radicals.

PATENT


10. (Previously presented) The composition of Claim 3 wherein the abstractable ligands are chloride, bromide, iodide, methyl, ethyl, propyl, butyl, pentyl, hexyl, heptyl, octyl, nonyl, decyl, undecyl, dodecyl, tridecyl, tetradecyl, pentadecyl, hexadecyl, heptadecyl, octadecyl, nonadecyl, eicosyl, heneicosyl, docosyl, tricosyl, tetracosyl, pentacosyl, hexacosyl, heptacosyl, octacosyl, nonacosyl, triacontyl, hydride, phenyl, benzyl, phenethyl, tolyl, methoxy, ethoxy, propoxy, butoxy, dimethylamino, diethylamino, methylethylamino, phenoxy, benzoxy, allyl, 1,1-dimethyl allyl, 2-carboxymethyl allyl, acetylacetonate, 1,1,1,5,5,5-hexa-fluoroacetylacetonate, 1,1,1-trifluoro-acetylacetonate, or 1,1,1-trifluoro-5,5-di-methylacetylacetonate radicals.
11. (Currently amended) The composition of Claim 3 wherein at least one of the abstractable ~~ligand~~ ligands is chloride.
12. (Currently amended) The composition of Claim 1 wherein the at least one monomer comprises styrene, vinyl styrene, an alkyl styrene, isobutylene, isoprene, or butadiene.
13. (Original) The composition of Claim 12 wherein the one or more monomers comprise styrene.
14. (Previously presented) The composition of Claim 1 wherein the free radical initiator is selected from the group consisting of azo initiators or peroxides.
15. (Previously presented) The composition of Claim 3 wherein the free radical initiator is selected from the group consisting of dialkyldiazenes, hyponitrites, diacyl peroxides, dialkyl peroxydicarbonates, peresters, alkyl hydroperoxides, dialkyl peroxides, or inorganic peroxides.
16. (Previously presented) The composition of Claim 15 wherein the free radical initiator is selected from the group consisting of 2,2'-azobis(2-methylpropanenitrile), 1,1-

PATENT



azobis(1-cyclohexanenitrile), 4,4'-azobis(4-cyanovaleric acid), triphenylmethy lazobenzene, di-t-butyl hyponitrite, dicumyl hyponitrite, dibenzoyl peroxide, didodecanoyl peroxide, diacetyl peroxide, diisopropyl ester, dicyclohexyl ester, cumyl hydroperoxide, t-butyl hydroperoxide, dicumyl peroxide, di-t-butyl peroxide, hydrogen peroxide, and persulfate initiators.

17. (withdrawn) A catalyst system comprising the reaction product of the composition of Claim 1 and an activator.
18. (withdrawn) The catalyst system of Claim 17 wherein the activator is selected from alumoxanes, aluminum alkyls, alkyl aluminum halides, alkylaluminum alkoxides, discrete ionic activators, and Lewis acid activators.
19. (withdrawn) The catalyst system of Claim 18 wherein the activator is selected from methylalumoxane, modified methylalumoxane, ethylalumoxane, trimethyl aluminum, triethyl aluminum, triisopropyl aluminum, diethyl aluminum chloride, alkylaluminum alkoxides, ammonium borate salts, phosphonium borate salts, triphenyl carbenium borate salts, ammonium aluminate salts, phosphonium aluminate salts, triphenyl carbenium aluminate salts, trisarylborane acids, and polyhalogenated heteroborane anions.
20. (Currently amended) A composition comprising the product of combining, in the presence of a free radical initiator, a catalyst precursor and at least one monomer wherein the monomer is polymerizable by free-radical polymerization. ~~The composition of Claim 1~~ wherein the catalyst precursor is represented by one of the following formulas:


PATENT




PATENT





PATENT




PATENT




PATENT




PATENT



PATENT



PATENT



wherein

- (a) X are the same or different abstractable ligand ~~D or E~~;
- (b) Each R, R', and R'' are independently selected from hydrogen or a hydrocarbyl group provided at least one of R, R', and R'' can be polymerized by a free radical initiator;
- (c) TM is ~~[[a]]~~ titanium;
- (d) n is an integer from 0-3; and
- (e) Pn is a Group-14-15 atom.

21. (withdrawn) An olefin polymerization method comprising the steps of combining an olefin with the composition of Claim 1, and an activator.
22. (Currently amended) An olefin polymerization method comprising combining the composition of ~~compositional~~ Claim 3 with an olefin and an activator, where
 - (a) the olefin monomer, and the catalyst and the activator are combined under polymerization conditions comprising:
 - (i) slurry polymerization conditions wherein slurry polymerization conditions comprise:

PATENT

- a reaction temperature of 0-120 °C;
- a reaction pressure of 103-5068 kPa gauge;
- a reaction media selected from C₃-C₇ alkanes; and
- a primary monomer concentration of 1-10 wt% based on the total weight of monomer plus media;

or

(ii) gas-phase polymerization conditions wherein gas-phase polymerization conditions comprise:

- a reaction temperature of 30-120 °C;
- a reaction pressure of 69 kPa-3.5 MPa gauge; and
- a primary monomer partial pressure of 138 kPa-2.1 MPa;




or

(iii) solution polymerization conditions wherein solution polymerization conditions comprise:

- a reaction temperature of 0-120 °C;
- a reaction pressure of 103-5068 kPa; and
- a solvent selected from toluene, benzene, xylene, or hexane.

23. (Currently amended) A composition comprising a bifunctional metallocene catalyst comprising the product of combining, in the presence of a free radical initiator, two or more catalyst precursors and at least one monomer wherein the monomer is polymerizable by free-radical polymerization, and wherein the catalyst precursors are represented by at least one of the formulas:

PATENT




wherein

- (a) each M is a Group 4 ~~Group 3-10~~ metal;
each M¹ is Group 4 ~~Group 3-10~~ metal;
- (b) L_A is a substituted or unsubstituted, cyclopentadienyl or heterocyclopentadienyl ligand connected to M or M¹ wherein L_A comprises R;
- (c) L_B is
 - (i) a ligand as defined for L_A but selected independently of L_A, or
 - (ii) J, a heteroatom ligand connected to M, wherein J comprises comprising a Group-14-15 atom and 0-2 of R";
- (d) T is a bridging group that connects L_A and L_B or that connects L_A and J and comprises a Group-13-to-16 element and 0-2 of R'; and
- (e) D and E are the same or different abstractable ligands,

wherein each R, R', and R" are independently hydrogen or a hydrocarbyl group provided at least one of R, R', and R" can be polymerized by a free radical initiator, provided that when M¹ is Zr, L_A is substituted at more than one carbon atom, and wherein the two or more catalyst precursors each have a different Group 4 metal.

PATENT

24. (Currently amended) A composition comprising the product of combining, in the presence of a free radical initiator, a catalyst precursor and at least one monomer wherein the monomer is polymerizable by free-radical polymerization, and wherein the catalyst precursor is represented by one of the formulas:



wherein


- (a) M is a ~~Group 3-10~~ Group 4 metal;
- (b) L_A is a substituted or unsubstituted, cyclopentadienyl or heterocyclopentadienyl ligand connected to M, wherein L_A comprises R;
- (c) J is a heteroatom ligand ~~connected to M, wherein J comprises~~ comprising a Group-14-15 atom and 0-2 of R";
- (d) T is a bridging group that connects L_A and L_B and comprises a Group-13-to-16 element and 0-2 of R'; and
- (e) D and E are the same or different abstractable ligands,

wherein each R, R', and R" are independently hydrogen or a hydrocarbyl group provided at least one of R, R', and R" can be polymerized by a free radical initiator.

25. (Currently amended) The composition of Claim 24 wherein the at least one monomer comprises styrene, vinyl styrene, an alkyl styrene, isobutylene, isoprene, or butadiene.
26. (Previously presented) The composition of Claim 24 wherein the one or more monomers comprise styrene.
27. (Currently amended) The composition of Claim 24 wherein the free radical initiator is selected from the group consisting of azo initiators [[or]] and peroxides.

PATENT

28. (Currently amended) The composition of Claim 24, wherein M is a ~~Group 4 metal~~ zirconium.
29. (Previously presented) The composition of Claim 24, wherein M is titanium.
30. (Previously presented) A composition comprising the product of combining, in the presence of a free radical initiator, a catalyst precursor and at least one monomer wherein the monomer is polymerizable by free-radical polymerization, and wherein the catalyst precursor is represented by one of the formulas:



wherein

- (a) M is a Group 3, or Group 5–10 metal;
 M' is a Group 3, or Group 5–10 metal;
- (b) L_A is a substituted or unsubstituted, cyclopentadienyl or heterocyclopentadienyl ligand connected to M wherein L_A comprises R;
- (c) L_B is
- (i) a ligand as defined for L_A but selected independently of L_A , or

PATENT

- (ii) J, a heteroatom ligand connected to M, wherein J comprises a Group-14-15 atom and 0-2 of R";
- (d) T is a bridging group that connects L_A and L_B and comprises a Group-13-to-16 element and 0-2 of R'; and
- (e) D and E are the same or different abstractable ligands,

wherein each R, R', and R" are independently hydrogen or a hydrocarbyl group provided at least one of R, R', and R" can be polymerized by a free radical initiator.

31. (Currently amended) The composition of Claim 30, wherein the at least one monomer comprises styrene, vinyl styrene, an alkyl styrene, isobutylene, isoprene, or butadiene.
32. (Previously presented) The composition of Claim 30, wherein the one or more monomers comprise styrene.
33. (Currently amended) The composition of Claim 30, wherein the free radical initiator is selected from the group consisting of azo initiators [[or]] and peroxides.

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☐ FADED TEXT OR DRAWING
- ☐ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☐ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☒ OTHER: Black dots

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.